

METZ 33-VG

TROWEL APPLIED EPOXY TOPPING



DESCRIPTION:

Metz 33-VG is a 100% solids trowel applied epoxy topping for vertical surfaces, applied at a thickness of 3 - 8 mm.

Metz 33-VG is used in conjunction with Metz 33-TG and can be used in a wide variety of food processing areas, as it resists food acids, fats, oils and cleaning compounds.

FEATURES AND BENEFITS:

- **Chemical resistance**
Excellent resistance to a wide range of acids, alkalis, solvents, oils and fats. Refer Metz Chemical Resistance Chart.
- **Excellent adhesion**
Tenacious bond to correctly prepared concrete surfaces.
- **Solventless**
100% solids system.
- **Cures under adverse conditions**
Cures at temperatures down to 5°C and high relative humidity.
- **Easily cleaned, slip resistant surface**
- **High strength**

RECOMMENDED:

As a monolithic topping to protect concrete against chemical and mechanical attack.

- Dairies and Milk Products processing
- Food Processing plants
- Breweries and Soft Drink plants
- Meat and Poultry plants
- Confectionery plants
- Chemical plants

NOT RECOMMENDED:

- For areas subject to spillages of strong solvents or concentrated organic or oxidising acids. Refer Metz (93PU-VG or Metz 33EN-VG).
- For thickness above 8mm in one application.

PHYSICAL PROPERTIES: (Typical Values)

Density:	1.8 - 1.9 g/cm ³
Compressive Strength:	100 MPa
Adhesion to concrete (ASTM C1583)	>1.5 MPa (concrete failure)
Flexural Strength:	35 MPa
Coefficient of Thermal Expansion, per °C:	35 x 10 ⁻⁶

COVERAGE: theoretical quantities (allow for wastage)

Metz Epoxy Primer	0.21kgs per sq metre at 0.2mm thickness
Metz 33-VG	5.5kgs per sq metre at 3mm thickness

APPLICATION TEMPERATURE:

For optimum results, maintain a temperature of 5°C to 30°C on air and substrate and components during mixing, application and curing

At temperatures below 5°C the application becomes more difficult and curing is retarded. At temperature above 30°C the working time decreases.



METZ 33-VG

TROWEL APPLIED EPOXY TOPPING



INSTRUCTIONS FOR USE

1. Temperature of Working Area

For optimum results, maintain a temperature of 5°C to 30°C on air and substrate and components during application and curing.

At temperatures below 5°C, the application becomes more difficult and curing is retarded.

At temperatures above 30°C, the working time decreases.

Application in direct sunlight and rising surface temperatures may result in blistering of the coating due to expansion of entrapped air or moisture in the substrate.

2. Surface Preparation

All surfaces must be clean, dry and free from oil, grease, water and other contaminants which may inhibit bond.

Remove all standing water. For best results surfaces should be dry. Concrete on grade should utilise a waterproof barrier behind.

(i) New Concrete

New concrete should have attained a compressive strength of 20 MPa minimum and be at least 28 days old. Surface must be free from laitance, form oils and curing compounds. Abrasive blast or high-pressure water blast to remove laitance and provide a uniform, textured surface.

(ii) Old Concrete

Concrete must be sound. Remove laitance, old paints, protective coatings and attacked or deteriorated concrete.

Chemically clean surface to remove any contaminants.

Abrasive blast or high-pressure water blast to remove laitance and provide a uniform, textured surface.

All structural cracks should be repaired and all slopes reestablished with approved repair material.

All surfaces must be vacuumed to remove any loose deposits and contamination.

(iii) Edge Detail

Wherever a free edge occurs (e.g. at the top of a cove), consideration should be given to cutting an anchoring and sealing groove in the substrate. This groove should be at least 6mm deep. Consult Metz for full details.

3. Mixing

a) Mixing Equipment

Mechanical mixing is required. A special resinous cements mixer or mortar mixer is suitable. Smaller quantities can be mixed using a heavy duty, slow speed drill with a suitable paddle. Consult Metz for details.

b) Mixing Proportions

Metz Epoxy Primer	By Weight	By Volume
Liquid	1.85	1.6
Hardener	1	1
Metz 33-VG	By Weight	By Volume
Liquid L1	2	2.20 litres
33 Hardener	1	1.17 litres
33-VG Powder	13	16kg (1 bag)

Note: The liquid to hardener ratios must not be altered under any circumstances.

The powder proportion can be altered by up to 10% to suit conditions

The addition of extra powder may result in a more porous surface.

c) Mixing Procedure

Remix liquids prior to use.

For Metz Epoxy Primer:

Mix liquid and hardener slowly and thoroughly for 1-2 minutes.

For Metz 33-VG:

Mix liquid and hardener together thoroughly for 1 - 2 minutes. Add powder gradually with constant stirring. Mix for 3 - 5 minutes. At the end of the mixing period, all material should be wetted out and uniform in colour and consistency. Material which has begun to set must be discarded. Do not add any solvent, additive or adulterant to any component or to the mixed material.

d) Pot Life at 20°C

Metz Epoxy Primer 70 minutes

Metz 33-VG 30 minutes

Note: Increase in temperature will decrease pot life, as will leaving mixed material in a large mass. Spread out material in a thin layer as soon as possible after mixing.

e) Clean Up

Mixing equipment, tools, etc., can be cleaned with Metz Cleaner, xylene, acetone or MEK prior to initial set of cement.

Note: Ensure you have the latest mixing instructions, refer www.metz.net.au for most current data sheet version.

4. Installation

(i) Metz Epoxy Primer

Apply to concrete using short nap adhesive roller or nylon bristle brush. Metz 33-VG can be placed whilst the primer is still tacky. If the primer has hardened, consult Metz. Do not apply Metz 33-VG.

(ii) Metz 33-VG

Material should be placed immediately after mixing. Do not let the mixed material remain in mixing vessel. Spread Metz 33-VG with a trowel to desired thickness (nominally 3mm). Ensure surface is closed and compacted. Finishing must be completed within 30 minutes of mixing at 20°C.

5. Setting/Curing

Initial set at 20°C: 12 hours

Full cure at 20°C: 7 days

Do not allow water, chemicals or traffic on the material surface for a minimum of 24 hours. For harsh chemical or physical environments, cure a minimum of 72 hours at 20°C prior to exposure.

6. Storage

Store in original containers in cool dry place. Under these conditions minimum shelf life is 12 months.

7. Safety Precautions

Liquid and Hardener

Use chemical goggles, PVC gloves and barrier cream.

Avoid contact with skin and eyes.

Powder

Avoid breathing dust. Ensure adequate ventilation.

For full safety precautions refer to Material Safety Data Sheets for all components.

Always ensure you have the latest data sheet version, refer www.metz.net.au

- The customer must comply strictly with the instructions contained in this product data sheet. Metz is not responsible for any advice or variations to this data sheet which are not confirmed in writing.
- If the customer has a claim against Metz in respect of any product supplied to the customer by Metz whether due to a fault in the product or the negligence or breach of contract by Metz or for any other reason:
 - Metz shall not be liable for any loss or damage including consequential loss or damage or loss of profits arising thereby;
 - Metz may at its option replace the defective product free of charge to the customer or refund all payments made to it by the buyer in respect of the defective product; and the maximum liability of Metz shall be the cost of replacing the defective product.

REV 12/10

**METZ SPECIALTY
MATERIALS PTY LTD**

A.C.N. 140 636 639

15A Stanton Road, Seven Hills NSW 2147
Facsimile: (02) 9671 4292 Phone: (02) 9671 1311

6 University Place, Clayton North, VIC 3168
Facsimile: (03) 9561 6944 Phone: (03) 9561 6144

Unit 16, 42 Smith Street, Capalaba QLD 4157
Facsimile: (07) 3823 5552 Phone: (07) 3823 5555

Distributor