

METZ KORODUR DRY-SHAKE TOPPING



DESCRIPTION:

Metz Korodur Dry-Shake Topping is a ready to use, dry-shake surface hardener consisting of Korodur 0/4 hard aggregate and Portland cement which greatly improves the abrasion and impact resistance of concrete floors. Korodur 0/4 is produced from high grade components comprising quartz and tough by-products from electro-metallurgical smelting processes. The engineered blend of different grain shapes and sizes results in an aggregate with high tensile and compressive strength and outstanding abrasion resistance. Over 200 million square metres of Korodur products have been installed world-wide.

FEATURES AND BENEFITS:

- Excellent abrasion resistance
- Resistant to petroleum, mineral oil and solvents.
- Non-rusting
- Easy to use during concreting process
- Quality Accreditation - The management system governing the development and manufacture of this product is proudly ISO9001:2015 certified.
- Frost and de-icer resistant
- Not electrostatically chargeable
- Non-dusting

RECOMMENDED:

As a dry-shake surface hardener applied to fresh concrete floors, both interior and exterior for

- Production areas and Workshops
- Parking areas and Hangars
- Loading docks and ramps etc.

In warehouses, cold stores, steel plants, parking garages, textile plants, food and beverage plants, paper mills, bus depots and large garages, waste water and sewerage treatment plants, automobile plants etc.

NOT RECOMMENDED:

- For areas exposed to acids, acid salts or other chemicals which attack Portland cement based concrete. Contact Metz for alternative products.
- For very heavy wear areas or superflat floors Korodur laid by the monolithic method should be used. Contact Metz for details.

PHYSICAL PROPERTIES:

Korodur 0/4 Aggregate (DIN 1100) (Wear resistant component)

	(Typical Values)
Mohs Hardness:	8 to 9
Compressive Strength, MPa	>80
Tensile Strength, MPa	>10
Size Range, mm	0 to 4

Metz Korodur Dry Shake Topping (applied @ 8kg/m²)

Abrasion Resistance: BS 8204 Class AR1 (Maximum wear depth 0.1 mm)
"Chaplin Test"

COVERAGE:

Type of traffic

Light	3 kgs/sq.metre
Light to Medium	5 kgs/sq.metre
Medium to Heavy	8 kgs/sq.metre

For very heavy traffic Korodur should be laid by the monolithic method - consult Metz for details.

COLOURS:

Standard Colour: Grey
Special Colours: Red, Black, Yellow and dark Grey manufactured to fulfill special orders.
Strength of final colour will depend upon application rate.



METZ KORODUR DRY-SHAKE TOPPING



INSTRUCTIONS FOR USE

1. Concrete Base

The base concrete should be placed in accordance with good concrete practice. The concrete should be mixed and laid according to the Cement and Concrete Association of Australia guidelines and shall have a minimum compressive strength of 30 MPa and a maximum slump of 75 mm. The water to cement ratio should be the minimum consistent with the need to produce a fully compacted concrete without excess water coming to the surface.

Note: The use of PCE (polycarboxylate ether) plasticizer in the concrete may adversely affect the bond of the Korodur Topping.

Pour and screed off base concrete. A level surface is essential. Treatment with a power float is recommended to achieve this, and to provide the correct cement concentration at the concrete surface. Puddles of cement and/or water must be removed.

2. Application

Refer to the recommended coverage figures on page 1. The Korodur Dry-Shake Topping is sprinkled in two stages. Two thirds of the dry mix is sprinkled evenly onto the base concrete. The dry mix is allowed to absorb water from the concrete. This is indicated by the surface becoming darker in colour.

A power float is then applied to the surface. The remaining one third of the dry mix is then applied to the surface. As soon as the surface has darkened, a second power floating is commenced.

3. Finishing

As soon as the concrete is in the setting phase, that is the surface is no longer shiny, power trowelling should commence. According to the required surface quality, power trowelling can be repeated with the trowelling blades at a progressively steeper angle. If no power float or power trowel is available, the application and finishing can be done manually. However, this should be avoided.

Note: For a more slip resistant surface keep trowelling blades as flat as possible.

4. Edge Reinforcement

To achieve an edge reinforcement, the freshly trowelled concrete is excavated at the edges to form a wedge-shaped cavity. Mix Korodur Dry-Shake Topping with water to produce a stiff plastic mortar and fill the excavated edge. The sprinkling job can then commence.

5. Joints

Joints should be formed in the Korodur Dry-Shake Topping sprinkled surface only where there are construction joints in the concrete base, or where specified by the Design Engineer.

6. Curing

It is essential that proper curing is carried out. Curing should commence as soon as the surface has hardened sufficiently to prevent damage. Carry out curing according to normal concrete practice.

Metz Korotex curing compound is available on a project basis.

7. Storage

Store in original containers in cool dry place. Under these conditions minimum shelf life is 12 months.

8. Safety Precautions

Avoid breathing dust. Allow adequate ventilation. Avoid contact with skin and eyes.

For fully safety precautions refer to the Safety Data Sheet for each component.

Always ensure you have the latest data sheet version, refer www.metz.net.au

1. The customer must comply strictly with the instructions contained in this product data sheet. Metz is not responsible for any advice or variations to this data sheet which are not confirmed in writing.
2. If the customer has a claim against Metz in respect of any product supplied to the customer by Metz whether due to a fault in the product or the negligence or breach of contract by Metz or for any other reason:
 - a) Metz shall not be liable for any loss or damage including consequential loss or damage or loss of profits arising thereby;
 - b) Metz may at its option replace the defective product free of charge to the customer or refund all payments made to it by the buyer in respect of the defective product; and the maximum liability of Metz shall be the cost of replacing the defective product.

REV 11/19

METZ SPECIALTY MATERIALS PTY LTD

A.C.N. 140 636 639

15A Stanton Road, Seven Hills NSW 2147
Facsimile: (02) 9671 4292 Phone: (02) 9671 1311

6 University Place, Clayton North, VIC 3168
Facsimile: (03) 9561 6944 Phone: (03) 9561 6144

Unit 16, 42 Smith Street, Capalaba QLD 4157
Facsimile: (07) 3823 5552 Phone: (07) 3823 5555

Distributor